



8 Segment Transitionals

Blue Star Diamond Technology

The Premium 8 Segment Transitionals result in a superior floor with reduced steps. Designed to transition from a metal bond diamond grinding process to a resin polishing process. Can run on medium and large planetary and rotary machines. Use Soft Grade with Very Hard Concrete and Standard Grade on most other types.



American Concrete Institute



PRODUCT FEATURES

- Reduces steps
- Mounts with velcro or boss/velcro
- Available in 30-400 grit
- Can be used wet or dry
- Long life (15,000-25,000 sq. ft.)



Item #	Size	Description	Boss	Grit	Product Hardness	Concrete Hardness
7155	3"	8 Segment Transitional	No Boss	30	Standard	Soft Med Hard
7156	3"	8 Segment Transitional	No Boss	50	Standard	Soft Med Hard
7157	3"	Premium Transitional	No Boss	100	Standard	Soft Med Hard
7241	3"	8 Segment Transitional	No Boss	200	Standard	Soft Med Hard
7158	3"	8 Segment Transitional	No Boss	400	Standard	Soft Med Hard
7151	3"	8 Segment Transitional	With Boss	30	Standard	Soft Med Hard
7152	3"	8 Segment Transitional	With Boss	50	Standard	Soft Med Hard
7153	3"	8 Segment Transitional	With Boss	100	Standard	Soft Med Hard
7259	3"	8 Segment Transitional	With Boss	200	Standard	Soft Med Hard
7154	3"	8 Segment Transitional	With Boss	400	Standard	Soft Med Hard
7228	3"	8 Segment Transitional	No Boss	30	Soft	Very Hard
7230	3"	8 Segment Transitional	No Boss	50	Soft	Very Hard
7232	3"	8 Segment Transitional	No Boss	100	Soft	Very Hard
7261	3"	8 Segment Transitional	No Boss	200	Soft	Very Hard
7227	3"	8 Segment Transitional	With Boss	30	Soft	Very Hard
7229	3"	8 Segment Transitional	With Boss	50	Soft	Very Hard
7231	3"	8 Segment Transitional	With Boss	100	Soft	Very Hard
7260	3"	8 Segment Transitional	With Boss	200	Soft	Very Hard



BSDdiamond.com
BSDsales@BorideAbrasives.com

PHONE 231.929.2121
 TOLL FREE 800.662.0336
 FAX 231.943.2852




Made in the USA

BORIDE
 Engineered Abrasives

2615 Aero Park Drive | Traverse City, MI 49686

GRIND • HONE • POLISH • FINISH



				30	50	80	100	200	270	400	800	1500	3000	Concrete Hardness
EASY EDGE	4"			◆	◆		◆		◆	◆				Soft Medium Hard Very Hard
	5"			◆	◆		◆		◆	◆				
	6"			◆	◆		◆		◆	◆				
	7"			◆	◆		◆		◆	◆				
EDGE FLEX	5"			◆	◆		◆		◆	◆	◆	◆		
	7"			◆	◆		◆		◆	◆	◆	◆		
BSD CORNER TOOL	Triangle			◆	◆		◆	◆		◆				
STANDARD Bond	PREMIUM TRANSITIONAL	3"	NO Boss	◆	◆		◆	◆		◆				Soft Medium Hard
		3"	WITH Boss	◆	◆		◆	◆		◆				
		2"	NO Boss	◆	◆		◆	◆		◆	◆	◆		
		2"	WITH Boss	◆	◆		◆	◆		◆	◆	◆		
	4 SEG FIRST CUT	3"	NO Boss	30/40	60/80	120/140								Hard
		3"	WITH Boss	30/40	60/80	120/140								
	BSD	3"	NO Boss	◆	◆	◆	◆	◆		◆	◆	◆		Soft Medium
		3"	WITH Boss	◆	◆	◆	◆	◆		◆				
	Resins	3"	(Dry and Wet)							◆	◆	◆	◆	Soft Medium Hard Very Hard
		2"	(Dry Only)							◆	◆	◆	◆	
	BSD Power Trowel PAD	11"		◆	◆	◆	◆	◆		◆	◆	◆	◆	Soft Medium Hard Very Hard
		14"		◆	◆	◆	◆	◆		◆	◆	◆	◆	
SOFT Bond	PREMIUM 8 SEGMENT	3"	NO Boss	◆	◆		◆	◆						Very Hard
		3"	WITH Boss	◆	◆		◆	◆						
	4 SEG FIRST CUT	3"	NO Boss	30/40	60/80	120/140								
		3"	WITH Boss	30/40	60/80	120/140								
	BSD	3"	NO Boss	◆	◆	◆	◆	◆		◆				Hard
		3"	WITH Boss	◆	◆	◆	◆	◆		◆				

S

Soft
Concrete
2-3 MOHS
< 3000 PSI

M

Medium
Concrete
3-5 MOHS
3000-4000 PSI

H

Hard
Concrete
5-7 MOHS
4500-6000 PSI

VH

Very Hard
Concrete
7-9 MOHS
>6000 PSI